

## Williamsburg Handmade Oil Colors Dry Time Chart

Fast	Medium		Slow	Very Slow
1-2	2-7		5-14	10-21+
Bohemian Green Earth	Bismuth Vanadate Yellow	Persian Rose	Alizarin Orange	Alizarin Crimson
Brown Ochre	Brilliant Yellow Extra Pale	Perylene Crimson	Cadmium Orange	Alizarin Yellow
Brown Pink	Brilliant Yellow Pale	Provence Violet Reddish	Cadmium Red Deep	Carl's Crimson
Brown Umber	Cadmium Lemon	Pyrrrole Red	Cadmium Red Purple	Egyptian Violet
Burnt Sienna	Cadmium Red Light	Quinacridone Goldish Brown	Cadmium Red Vermilion	Fanchon Red
Burnt Umber	Cadmium Red Medium	Red Ochre	Cobalt Teal	Graphite Gray
Cadmium Green	Cadmium Yellow Deep	SF Italian Terra Verte	Iridescent Bronze	Indanthrone
Cadmium Green Light	Cadmium Yellow Extra Deep	SF Cerulean Blue French	Iridescent Pale Gold	Indian Yellow
Cerulean Blue French	Cadmium Yellow Light	SF Cobalt Violet Light	Iridescent Pewter	Permanent Orange
Cobalt Blue Deep	Cadmium Yellow Medium	SF Flake White	Italian Pompeii Red	Pyrrrole Orange
Cobalt Teal Deep	Canton Rose	SF French Ardoise Grey	Lamp Black	Zinc White
Cobalt Turquoise Bluish	Cerulean Blue	SF Porcelain White	Permanent Green Light	
Cobalt Turquoise Greenish	Chromium Oxide	SF Titanium White	Permanent Yellow Deep	
Cobalt Yellow	Cinnabar Green Light	SF Ultramarine Blue	Phthalo Blue	
Courbet Green	Cobalt Blue	SF Ultramarine Blue French	Provence Violet Bluish	
Cyprus Orange	Cobalt Violet Deep	Sevres Blue	Quinacridone Magenta	
Dutch Brown	Cobalt Violet Light	Titan Buff	Quinacridone Red	
Earth Green	Cold Black	Titanium-Zinc White	Quinacridone Violet	
French Burnt Umber	Davy's Gray Deep	Ultramarine Blue	SF Ultramarine Pink	
German Earth	Dianthus Pink	Ultramarine Blue French	SF Ultramarine Violet	
Indigo	Flake White	Van Dyke Brown	Ultramarine Pink	
Italian Black Roman Earth	French Brown Ochre	Veronese Green	Ultramarine Violet	
Italian Green Ochre	French Burnt Ochre	Yellow Ochre Domestic		
Italian Pozzuoli	French Cassel Earth			
Italian Raw Sienna	French Rouge Indian			
Italian Raw Umber	French Light Sienna			
Italian Rosso Veneto	French Noir Indien			
Italian Terra Rosa	French Ochre Havane			
Italian Terra Verte	French Raw Sienna			
Italian Yellow Ochre	French Raw Umber			
Jaune Brilliant	French Rouge Indian			
Manganese Violet	French Terre Verte			
Mars Orange	Green Gold			
Mars Red	Interference Blue			
Mars Red Light	Interference Green			
Mars Yellow Deep	Interference Red			
Neutral Gray N2	Interference Violet			
Neutral Gray N4	Iridescent Copper			
Neutral Gray N6	Iridescent Pearl White			
Neutral Gray N8	Iridescent Silver			
Olive Green	Italian Burnt Sienna			
Payne's Gray Violet	Italian Lemon Ochre			
Permanent Green	Italian Orange Ochre			
Phthalo Green	Italian Pink			
Phthalo Green Yellowish	Ivory Black			
Phthalo Turquoise	King's Blue			
Prussian Blue	Mars Black			
Raw Sienna	Mars Violet			
Raw Umber	Mars Yellow Light			
Red Umber	Montserrat Orange			
Sap Green	Naples Yellow			
Spanish Earth	Naples Yellow Italian			
Stil de Grain	Naples Yellow Reddish			
Titanium White	Nickel Azo Yellow			
Transparent Red Iron Oxide	Nickel Yellow			
Transparent Yellow Iron Oxide	Payne's Grey			
Turkey Umber	Permanent Crimson			
Turquoise	Permanent Lemon			
Unbleached Titanium	Permanent Red Orange			
Unbleached Titanium Pale	Permanent Yellow Green			
Viridian	Permanent Yellow Light			
Yellow Ochre Burnt	Permanent Yellow Medium			

The following chart shows the relative drying rates of Williamsburg Handmade Oil Colors. Your actual dry times will be affected by how thickly the paint is applied, the absorbency of the surface, and even the surrounding colors.

As a point of reference, here is what you can expect for a 3 mil film (approximately the thickness of paper) applied to a relatively non-absorbent surface:

**FAST:**

**MEDIUM:**

**SLOW:**

**VERY SLOW:**

**1-2 Days**

**2-7 Days**

**5-14 Days**

**10-21+ Days**

Key:

SF = Safflower

Updated 05/15/18